

BIOLLOY KG320

Polylactic Acid + ABS

Techno Polymer Co, Ltd.

Message:

BIOLLOY KG320 is a Polylactic Acid + ABS (PLA+ABS) product. It is available in Asia Pacific or North America.

Characteristics include:

Flame Rated

Eco-Friendly/Green

Impact Resistant

General Information			
UL YellowCard	E54297-101074841		
Features	General Purpose		
	High Impact Resistance		
	Renewable Resource Content		
UL File Number	E54297		
Physical	Nominal Value	Unit	Test Method
Density	1.13	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	20	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.60	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	116		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	55.0	MPa	ISO 527-2
Flexural Modulus	2630	MPa	ISO 178
Flexural Stress	82.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	31	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	78.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	66.0	°C	ISO 75-2/A
Flammability	Nominal Value		Test Method
Flame Rating (ALL)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	75.0	°C	
Rear Temperature	190 to 260	°C	
Middle Temperature	190 to 260	°C	
Front Temperature	190 to 260	°C	
Mold Temperature	40.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

