

LNP™ STAT-KON™ EE004 compound

Polyether Imide
SABIC Innovative Plastics

Message:

LNP STAT-KON EE004 is a compound based on Polyetherimide resin containing 20% Carbon Fiber. Added features of this material include: Electrically Conductive.
Also known as: LNP* STAT-KON* Compound EC-1004
Product reorder name: EE004

General Information			
UL YellowCard	E121562-101344695		
Filler / Reinforcement	Carbon Fiber,20% Filler by Weight		
Features	Electrically Conductive		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955, ISO 294-4
Flow : 24 hr	0.10 to 0.30	%	
Across Flow : 24 hr	0.30 to 0.50	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	14500	MPa	ISO 527-2/1
Tensile Strength			
Break	170	MPa	ASTM D638
Break	175	MPa	ISO 527-2
Tensile Strain			
Yield	2.0	%	ISO 527-2
Break	2.0	%	ASTM D638
Flexural Modulus			
--	12300	MPa	ASTM D790
--	12000	MPa	ISO 178
Flexural Strength			
--	260	MPa	ASTM D790
--	250	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	59	J/m	ASTM D256
23°C ¹	7.0	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	530	J/m	ASTM D4812

23°C ²	30	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	213	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ³	210	°C	ISO 75-2/Af
CLTE			ISO 11359-2
Flow : -40 to 40°C	1.0E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.0E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+6	ohms	ASTM D257
Volume Resistivity	1.0E+2 to 1.0E+6	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.500 mm, Testing by SABIC)	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	343 to 354	°C	
Middle Temperature	354 to 366	°C	
Front Temperature	366 to 377	°C	
Processing (Melt) Temp	360 to 366	°C	
Mold Temperature	121 to 149	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	60 to 100	rpm	
NOTE			
1.	80*10*4		
2.	80*10*4		
3.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT