

# Axiall PVC 8852

Flexible Polyvinyl Chloride

Axiall Corporation

## Message:

General purpose compound recommended for extrusion applications. Contains a biocide and is UV stabilized.

General Information			
Additive	Biocide		
	UV Stabilizer		
Features	General Purpose		
Uses	General Purpose		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.37	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	85		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	16.9	MPa	
100% Strain	9.31	MPa	
Tensile Elongation (Break)	330	%	ASTM D638
Extrusion	Nominal Value	Unit	
Melt Temperature	177	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

  
WECHAT