

# Kemcor MD 6550

Linear Medium Density Polyethylene

Qenos Pty Ltd

Message:

MD 6550 is manufactured us the fluidized bed process.  
This resin is manufactured to conform to the requirements for unrestricted food contact of AS 2070 Part 1 (1992).

General Information	
Features	Good Impact Resistance
	Good Processability
	Good Toughness
	High ESCR (Stress Crack Resist.)
	High Rigidity
Uses	Automotive Applications
	Household Goods
	Toys
Appearance	Natural Color
Forms	Pellets
Processing Method	Dip Coating
	Injection Molding
	Rotational Molding

Physical	Nominal Value	Unit	Test Method
Density	0.938	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	6.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	18.0	MPa	
Break	25.0	MPa	
Tensile Elongation (Break)	800	%	ASTM D638

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

