

Statimax 810

Polybenzimidazole
Polymics, Ltd.

Message:
Polybenzimidazole (PBI), Electrostatic Dissipative (ESD)

General Information			
Features		ESD Protection	
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.49	g/cm ³	ASTM D792
Water Absorption (23°C, 24 hr)	0.40	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	9000	MPa	ASTM D638
Tensile Strength	200	MPa	ASTM D638
Flexural Modulus	9700	MPa	ASTM D790
Flexural Strength	260	MPa	ASTM D790
Compressive Modulus	8300	MPa	ASTM D695
Compressive Strength	430	MPa	ASTM D695
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	438	°C	ASTM D648
Glass Transition Temperature	427	°C	ASTM D3418
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+4 to 1.0E+6	ohms	ASTM D257

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT