

Geon™ Vinyl Rigid Extrusion L4857

Rigid Polyvinyl Chloride

PolyOne Corporation

Message:

Geon™Vinyl Rigid Extrusion L4857 is a rigid PVC product. It can be processed by extrusion and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Typical application areas are: outdoor applications.

Features include:

low gloss

Impact resistance

good weather resistance

General Information			
Features	Gloss, low		
	Impact resistance, high		
	Good weather resistance		
Uses	Outdoor application		
	Profile		
Forms	Cube		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm³	ASTM D792
PVC Cell Classification	1-41432-33		ASTM D4216
PVC Cell Classification	16334		ASTM D1784
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 15 sec)	83		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	2450	MPa	ASTM D638
Tensile Strength ² (Yield)	42.7	MPa	ASTM D638
Flexural Modulus	2830	MPa	ASTM D790
Flexural Strength	77.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256A
Transverse flow: 23°C, 3.18mm, molded	200	J/m	ASTM D256A
Flow: 23°C, 3.18mm, molded	220	J/m	ASTM D256A
Drop Impact Resistance			ASTM D4226
23°C ³	53.4	J/cm	ASTM D4226
23°C ⁴	187	J/cm	ASTM D4226
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	72.8	°C	ASTM D648

CLTE - Flow	5.9E-5	cm/cm/°C	ASTM D696
Additional Information	Nominal Value		
Ease of Sizing	Good		
注释:分档是采用注塑模制样品进行缺口摆锤冲击试验确定的.			
Extrusion	Nominal Value	Unit	
Melt Temperature	182 - 193	°C	
NOTE			
1.	Type 1, 5.1 mm/min		
2.	Type 1, 5.1 mm/min		
3.	Procedure A, C.125 Throwing		
4.	Procedure B, C.125 Throwing		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

