

# Nylene® PAC6-135

Polyamide 66/6 Copolymer

Custom Resins Group

Message:

Nylon 6,6/6 copolymer. Nylene PAC6-135 is suitable for use in extrusion, and film applications  
Has the heat and chemical resistance of nylon, with the lower crystallinity typical of type 6,6/6 grades  
Suitable for high clarity film

General Information			
Features	Copolymer		
	Good Chemical Resistance		
	High Clarity		
Uses	Film		
Processing Method	Extrusion		
	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12	g/cm <sup>3</sup>	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	68.9	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	300	%	ASTM D638
Flexural Modulus (23°C)	2760	MPa	ASTM D790
Thermal	Nominal Value	Unit	Test Method
Peak Melting Temperature	195	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT