

Pinnacle PP 5135C3

Polypropylene Random Copolymer

Pinnacle Polymers

Message:

35 MELT FLOW CLARIFIED RANDOM COPOLYMER FOR INJECTION MOLDING

Pinnacle Polymers Polypropylene 5135C3 is made via UNIPOL™ PP technology, which utilizes gas-phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This product is intended for injection molding applications that require fast cycle time, improved color, enhanced processability and excellent clarity.

The 5135C3 product provides:

- Reduced cycle-time
- Improved color
- Improved processability
- Excellent lot-to-lot consistency
- Excellent impact resistance

Pinnacle's polypropylene, as marketed by Pinnacle Polymers, in natural, uncolored pellet form complies with appropriate requirements of CFR Title 21, Part 177, Subpart B, Section 177.1520 (c) 3.1a entitled "Olefin Polymers" of the Food Additives Amendment of 1958 to the United States Food, Drug and Cosmetic Act of 1938.

| General Information | | | |
|---|-----------------------------|----------|-------------|
| Additive | Clarifier | | |
| Features | Fast Molding Cycle | | |
| | Food Contact Acceptable | | |
| | Good Processability | | |
| | High Clarity | | |
| | High Impact Resistance | | |
| | Random Copolymer | | |
| Agency Ratings | FDA 21 CFR 177.1520(c) 3.1a | | |
| Forms | Pellets | | |
| Processing Method | Injection Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 0.900 | g/cm³ | ASTM D1505 |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg) | 35 | g/10 min | ASTM D1238 |
| Molding Shrinkage - Flow | 1.5 | % | ASTM D955 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ¹ (Yield, 3.20 mm, Injection Molded) | 26.2 | MPa | ASTM D638 |
| Tensile Elongation ² (Yield, 3.20 mm, Injection Molded) | 12 | % | ASTM D638 |
| Flexural Modulus - 1% Secant ³ (3.20 mm, Injection Molded) | 962 | MPa | ASTM D790A |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact ⁴ (23°C, 3.20 mm, Injection Molded) | 69 | J/m | ASTM D256 |

| Notched Izod Impact (Area) ⁵ (23°C, 3.20 mm, Injection Molded) | 6.80 | kJ/m ² | ASTM D256 |
|---|--------------------|-------------------|-------------|
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (0.45 MPa, Unannealed) | 71.0 | °C | ASTM D648 |
| Optical | Nominal Value | Unit | |
| Haze (1270 μm) | 9.0 | % | |
| Yellowness Index | < 10 | YI | |
| NOTE | | | |
| 1. | Type I, 51 mm/min | | |
| 2. | Type I, 51 mm/min | | |
| 3. | Type I, 1.3 mm/min | | |
| 4. | Type I | | |
| 5. | Type I | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

