

Hostacom X M2 U38

Polypropylene Copolymer

LyondellBasell Industries

Message:

Hostacom X M2 U38 is a Polypropylene Copolymer (PP Copolymer) product. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America. Typical application: Automotive. Primary characteristic: copolymer.

General Information			
Features	Copolymer		
Uses	Automotive Applications		
	Automotive Interior Parts		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
230°C/2.16 kg	16	g/10 min	
230°C/5.0 kg	67	g/10 min	
Melt Volume-Flow Rate (MVR)			ISO 1133
230°C/2.16 kg	18.0	cm ³ /10min	
230°C/5.0 kg	78.0	cm ³ /10min	
Molding Shrinkage	0.90 to 1.1	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	67.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant	2200	MPa	ISO 527-2
Tensile Stress (Yield)	27.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	5.0	%	ISO 527-2/50
Flexural Modulus - Secant	2400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	15	kJ/m ²	
0°C	40	kJ/m ²	
23°C	60	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	110	°C	ISO 75-2/B
1.8 MPa, Unannealed	64.0	°C	ISO 75-2/A
Vicat Softening Temperature	78.0	°C	ISO 306/A50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

