## ECP 2693

## Polyethylene Terephthalate Glycol Comonomer

TBA Electro Conductive Products Ltd.

## Message:

The new ECP 2000 series of static dissipative polymers have been formulated specifically for clean room environments where low offgassing, low particulate, contamination and washability are required. The compounds can be coloured.

The materials are permanently conductive and can be processed on conventional equipment. The products are humidity independent, aqueous washable and can be re-used.

Applications that are ideally suited for the compounds and in use commercially at customer sites include: packaging for electronic components, medical device packaging, in-process carriers, fixturing devices, chip rails, vacuum tubing and business machine components.

Because of their flexibility, the thermoplastic polyurethane (TPU) based alloys are also useful as softwall cleanroom materials, flexible packaging, hose and tubing, floor and table mats and other flexible cleanroom applications.

| General Information                   |                      |                   |
|---------------------------------------|----------------------|-------------------|
| Features                              | Conductive           |                   |
|                                       | Good Colorability    |                   |
|                                       | Good Flexibility     |                   |
|                                       | Humidity Independent |                   |
|                                       |                      |                   |
| Uses                                  | Business Equipment   |                   |
|                                       | Medical Packaging    |                   |
|                                       | Packaging            |                   |
|                                       | Tubing               |                   |
|                                       |                      |                   |
| Appearance                            | Opaque               |                   |
| Processing Method                     | Injection Molding    |                   |
|                                       | Thermoforming        |                   |
|                                       |                      |                   |
| Physical                              | Nominal Value        | Unit              |
| Density                               | 1.25                 | g/cm <sup>3</sup> |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 |                      |                   |
| kg)                                   | 5.0                  | g/10 min          |
| Mechanical                            | Nominal Value        | Unit              |
| Tensile Modulus                       | 1240                 | MPa               |
| Tensile Stress                        | 31.0                 | MPa               |
| Electrical                            | Nominal Value        | Unit              |
| Surface Resistivity                   | 1.0E+10              | ohms              |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

