

DynaPath™ C2245CFT

Polycarbonate
Polymer Dynamix

Message:

- Features:
- Electrical conductivity
 - Easy to mold
 - Great surface appearance
- Applications:
- Automotive
 - Industrial
 - Electrical/Electronics

General Information	
Filler / Reinforcement	Carbon Fiber,30% Filler by Weight PTFE Fiber,15% Filler by Weight
Features	Conductive Good Processability Good Surface Finish
Uses	Automotive Applications Electrical/Electronic Applications Industrial Applications

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.32	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	159	MPa	ASTM D638
Tensile Elongation (Break)	2.2	%	ASTM D638
Flexural Modulus	16100	MPa	ASTM D790
Flexural Strength	223	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	130	J/m	ASTM D256
Unnotched Izod Impact (23°C, 3.18 mm)	770	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	171	°C	ASTM D648

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

