

SQUARE® SSR8630-50AF/BF

Silicone

Shenzhen SQUARE Silicone Co., Ltd.

Message:

Oil self exudation solid silicone rubber for automobile coil linkspan

Product description

SSR8630-xxAF/BF is 2-part solid silicone rubber for making automobile coil linkspan, catalyzed by platinum, suitable for injection or compression molding process.

Key features

Good rebound properties, low deformation.

Good resistance to ageing and good weather resistance.

High tear strength and tensile strength.

Excellent thermal and cold stability (-60°C - 250°C)

Good electrical insulating property.

Oil self exudating property after being cured.

Application

Suitable for making oil self exudation automobile coil linkspan

General Information			
Features	High tensile strength Insulation Good tear strength Good weather resistance Thermal stability, good		
Uses	Application in Automobile Field		
Appearance	Clear/transparent		
Processing Method	Compression molding Injection molding		
Physical	Nominal Value	Unit	Test Method
Molding Shrinkage - Flow	2.0	%	JIS K6301
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	50		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Set ¹	6	%	ASTM D412
Tensile Strength	8.00	MPa	ASTM D412
Tensile Elongation (Break)	800	%	ASTM D412
Tear Strength ²	40.0	kN/m	ASTM D624
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Thermoset	Nominal Value	Unit	
Shelf Life	100	wk	
NOTE			

-
- | | |
|----|---------|
| 1. | C mould |
| 2. | B mould |
-

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

