

SABIC® Polyester TC 183

Polyethylene Terephthalate

Saudi Basic Industries Corporation (SABIC)

Message:

Textile Chips

General Information	
Uses	Filament
	Fiber
Forms	Particle
Processing Method	Filament extrusion
	Fiber (spinning) extrusion

Additional Information

Melting point, SABIC 0045: 252 - 258°C Moisture, SABIC 0059: < 0.2% w/w Intrinsic viscosity, SABIC 0041: 0.62-0.65 dl/gm Carboxyl end group, SABIC 0046: 15.0-30.0 Ash content, SABIC 0047: 0.30±0.05% w/w DEG content, SABIC 0055: 0.95-1.35% w/w Color (L), SABIC 0051, L-value: 92 - 98 Color (b), SABIC 0051, b-value: 2.0 - 5.0 Luster: Semi-Dull

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material
--

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

