

RTP 200 TFE 18 SI 2 HS

Polyamide 66

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.

General Information			
Additive	PTFE lubricant (18%)		
	Silicone lubricant (2%)		
	heat stabilizer		
Features	Thermal Stability		
	Lubrication		
RoHS Compliance	Contact manufacturer		
Appearance	Black		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.4	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.80	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2830	MPa	ASTM D638
Tensile Strength	62.1	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	2340	MPa	ASTM D790
Flexural Strength	97.9	MPa	ASTM D790
Compressive Strength	32.4	MPa	ASTM D695
Coefficient of Friction (With Metal-Dynamic)	0.060		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (6.35 mm)	43	J/m	ASTM D256
Unnotched Izod Impact (6.35 mm)	430	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	210	°C	ASTM D648
1.8 MPa, not annealed	104	°C	ASTM D648
CLTE - Flow	8.1E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.26	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.70		ASTM D150
Dissipation Factor (1 MHz)	0.015		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Additional Information			

The value listed as Flammability, UL 94, was tested in accordance with RTP test standards. Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 18mil/in. Tensile Elongation, ASTM D-638: 3-4% Flammability, ASTM D-635: B in/min. Wear Factor, K, ASTM D-3702: 10E-10in³/min/ft/lb/hr Coefficient of Friction, Dynamic, ASTM D-3702: 0.06 The wear factor and dynamic coefficient of friction were both tested on thrust washer apparatus at 300 FPM, 8500 PV, against 1141 Ryex steel of hardness 18-22 Rockwell C, 12-16 micro smoothness.

Injection	Nominal Value	Unit
Drying Temperature	79.4	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.20	%
Suggested Max Regrind	20	%
Rear Temperature	274 - 288	°C
Middle Temperature	274 - 288	°C
Front Temperature	274 - 288	°C
Mold Temperature	65.6 - 107	°C
Injection Pressure	68.9 - 103	MPa

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

