

SILVER® FT-1

Polyvinyl Chloride

Guangdong Silver Age Sci & Tech. Co., Ltd

Message:

SILVER® PVC for water pipe, entirely conforming to FDA, NSF and ACS, is of excellent mechanical and processing properties. In addition, the custom—made products should be developed by buyers ‘ requirements in order to meet special usage.

| General Information | | |
|--|------------------------|----------|
| Features | Good Processability | |
| Uses | Piping | |
| Agency Ratings | ACS Unspecified Rating | |
| | FDA Unspecified Rating | |
| | NSF Unspecified Rating | |
| Appearance | Natural Color | |
| Physical | Nominal Value | Unit |
| Specific Gravity | 1.38 | g/cm³ |
| Melt Mass-Flow Rate (MFR) (200°C/5.0 kg) | 7.0 | g/10 min |
| Hardness | Nominal Value | Unit |
| Durometer Hardness (Shore A) | 75 | |
| Mechanical | Nominal Value | Unit |
| Tensile Strength ¹ | 11.0 | MPa |
| Tensile Elongation (Break) | 390 | % |
| Thermal | Nominal Value | Unit |
| Brittleness Temperature | -30.0 | °C |
| NOTE | | |
| 1. | after aging | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT