

Miramid® SE35CW

Polyamide 66

BASF Leuna GmbH

Message:

Miramid® SE35CW is a Polyamide 66 (Nylon 66) material filled with 35% glass fiber. It is available in Europe for injection molding.

Important attributes of Miramid® SE35CW are:

Chemical Resistant

Crystalline

Fast Molding Cycle

Good Dimensional Stability

Good Stiffness

Typical applications include:

Automotive

Hose/Tubing

General Information				
Filler / Reinforcement	Glass Fiber,35% Filler by Weight			
Additive	Heat Stabilizer			
	Mold Release			
Features	Crystalline			
	Fast Molding Cycle			
	Fuel Resistant			
	Good Dimensional Stability			
	Good Flow			
	Good Stiffness			
	Grease Resistant			
	Heat Stabilized			
	High Rigidity			
	Oil Resistant			
	Solvent Resistant			
Uses	Automotive Applications			
	Tubing			
Forms	Granules			
Processing Method	Injection Molding			
Physical	Dry	Conditioned	Unit	Test Method
Density	1410	--	kg/m ³	ISO 1183 ¹
Water Absorption				ISO 62 ²
Saturation	4.8	--	%	
Equilibrium	1.4	--	%	
Viscosity number	145	--	cm ³ /g	ISO 307, 1157, 1628 ³

Mechanical	Dry	Conditioned	Unit	Test Method
Tensile modulus	11000	8600	MPa	ISO 527-2 ⁴
Tensile Stress (Break)	195	150	MPa	ISO 527-2 ⁵
Tensile Strain (Break)	3.0	5.0	%	ISO 527-2 ⁶
Flexural Stress ⁷	305	235	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy notched impact strength				ISO 179/1eA ⁸
-30°C	9.00	--	kJ/m ²	
23°C	11.0	13.0	kJ/m ²	
Charpy impact strength				ISO 179/1eU ⁹
-30°C	90.0	--	kJ/m ²	
23°C	90.0	95.0	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2 ¹⁰
0.45 MPa	250	--	°C	
1.8 MPa	250	--	°C	
Melting Temperature (DSC)	260	--	°C	ISO 3146
Electrical	Dry	Conditioned	Unit	Test Method
Volume resistivity	1.0E+13	1.0E+10	ohms·m	IEC 60093 ¹¹
Dielectric Constant (1 MHz)	3.50	5.70		IEC 60250
Dissipation Factor (1 MHz)	0.020	0.30		IEC 60250 ¹²
Comparative tracking index	450	--		IEC 60112 ¹³
Injection	Dry	Unit		
Processing (Melt) Temp	280 to 300		°C	
Mold Temperature	80.0 to 100		°C	

NOTE

1. Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

2. Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

3. Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

4. Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

5. Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

6. Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

7.	Typical values for uncoloured product at 23°C
8.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
9.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
10.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
11.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
12.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.
13.	Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

