

# RABALON® QE133AT

Thermoplastic Elastomer

Mitsubishi Chemical Performance Polymers, Inc.

## Message:

RABALON®QE133AT is a thermoplastic elastomer (TPE) material. This product is available in North America, Europe or Asia Pacific region. The processing method is injection molding.

RABALON®The typical application fields of QE133AT are: automobile industry

General Information			
Uses	Car interior parts		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	0.930	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	27	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	70		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (Break)	11.0	MPa	ISO 37
Tensile Elongation (Break)	660	%	ISO 37

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

