

# S&E; PVC G-3570

Polyvinyl Chloride  
S&E; Specialty Polymers, LLC

Message:

S & E PVC G-3570 is a polyvinyl chloride product. It is available in North America. Typical application areas are: consumer goods. The main characteristics are: good flexibility.

| General Information        |                  |                   |             |
|----------------------------|------------------|-------------------|-------------|
| Features                   | Good flexibility |                   |             |
|                            | General          |                   |             |
| Uses                       | General          |                   |             |
|                            | Footwear         |                   |             |
| Appearance                 | Available colors |                   |             |
|                            | Natural color    |                   |             |
| Forms                      | Particle         |                   |             |
| Physical                   | Nominal Value    | Unit              | Test Method |
| Specific Gravity           | 1.21             | g/cm <sup>3</sup> | ASTM D792   |
| Hardness                   | Nominal Value    | Unit              | Test Method |
| Durometer Hardness         |                  |                   | ASTM D2240  |
| Shaw A                     | 75               |                   | ASTM D2240  |
| Shaw A, 15 seconds         | 68               |                   | ASTM D2240  |
| Elastomers                 | Nominal Value    | Unit              | Test Method |
| Tensile Strength (Yield)   | 11.7             | MPa               | ASTM D412   |
| Tensile Elongation (Break) | 300              | %                 | ASTM D412   |
| Additional Information     |                  |                   |             |

Suggested Stock Temperature: 330-350°F Ross Flex, ASTM D1052, -20°F: 30000+

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT