

EPLAMID 66 GFS 50 HS NC

Polyamide 66
EPSAN Plastik SAN. ve TiC. A.S.

Message:

Polyamide 66, reinforced with 50% of glass fiber, heat stabilized, lubricated for injection moulding.
Eplamid 66 GFS 50 HS is used in all sectors of industry, offering a perfect balance of thermal and mechanical properties.
This product is available in natural and in colours on request.

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 50% filler by weight		
Additive		heat stabilizer		
		Lubricant		
Features		Thermal Stability		
		Lubrication		
Appearance		Available colors		
		Natural color		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.54	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Vertical flow direction: 3.00mm	0.40	--	%	ISO 294-4
Flow direction: 3.00mm	0.20	--	%	ISO 294-4
Moisture Content	0.20	--	%	ISO 15512
Ash Content	50	--	%	ISO 3451-4
Hardness	Dry	Conditioned	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	90	--		ISO 868
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	15000	14500	MPa	ISO 527-2/50
Tensile Stress (Break, 23°C)	220	210	MPa	ISO 527-2/50
Tensile Strain (Break, 23°C)	2.0	4.0	%	ISO 527-2/50
Flexural Modulus ¹ (23°C)	14200	13900	MPa	ISO 178
Flexural Stress ² (23°C)	270	250	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	18	20	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C)	17	18	kJ/m ²	ISO 180/1A

Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature ³ (1.8 MPa, Unannealed)	250	--	°C	ISO 75-2/A
Vicat Softening Temperature	255	--	°C	ISO 306/B120
Melting Temperature (DSC)	255	--	°C	ISO 3146
Flammability	Dry	Conditioned		Test Method
Flame Rating (1.60 mm)	HB	--		UL 94, IEC 60695-11-10, -20
Additional Information				
干燥 TEST CONDITIONS: Laboratory conditions are 23 ±2°C and 45-55 % RH.				
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	2.0 - 4.0		hr	
Processing (Melt) Temp	280		°C	
NOTE				
1.	2.0 mm/min			
2.	2.0 mm/min			
3.	120°C/h			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

