

Vydyne® R535H Black

Polyamide 66

Ascend Performance Materials Operations LLC

Message:

Vydyne R535H Black is general-purpose, heat-stabilized, hydrolysis-resistant, 35% glass-fiber reinforced PA66 resin. It is specifically designed to maximize the retention of physical properties when exposed to anti-freeze solutions at elevated temperatures. This product is also lubricated for improved flow and offers superior surface appearance.

Glass-reinforced Vydyne resins provide higher heat distortion temperature, resistance to creep and better dimensional stability when compared with unreinforced PA66. These products have good chemical resistance to a broad range of chemicals including gasoline, hydraulic fluids and most solvents. Vydyne R535H Black is heat-stabilized to minimize oxidative degradation of the polymer when exposed to elevated temperatures in service. This product provides improved retention of physical properties under exposure to long-term heat. Also, Vydyne R535H Black has excellent knit-line strength and fatigue resistance, which is essential for cycle testing with anti-freeze solutions.

Typical Applications/End Uses:

Vydyne R535H Black has been used successfully in a wide range of injection-molding engineering applications, including automotive clips, radiator end-tanks, parts of the air-conditioning and fuel distribution systems; electrical connectors, housings and bobbins; and industrial applications such as gears, bearing shells, covers and housings.

General Information				
UL YellowCard		E70062-249086		
Filler / Reinforcement		Glass Fiber,35% Filler by Weight		
Additive		Heat Stabilizer		
		Lubricant		
Features		Antifreeze Resistant		
		Fatigue Resistant		
		Gasoline Resistance		
		Good Chemical Resistance		
		Good Flow		
		Heat Stabilized		
		Hydrolysis Resistant		
		Lubricated		
		Solvent Resistant		
Uses		Automotive Under the Hood		
Agency Ratings		ASTM D 4066 PA012G35		
		ASTM D 6779 PA012G35		
UL File Number		E70062		
Appearance		Black		
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.41	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4

Across Flow : 2.00 mm	0.90	--	%	
Flow : 2.00 mm	0.40	--	%	
Water Absorption				ISO 62
23°C, 24 hr	0.80	--	%	
Equilibrium, 23°C, 50% RH	1.6	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	11600	8500	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	210	150	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.0	5.0	%	ISO 527-2
Flexural Modulus (23°C)	10500	7000	MPa	ISO 178
Flexural Stress (23°C)	300	205	MPa	ISO 178
Poisson's Ratio	0.40	--		ISO 527
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	11	12	kJ/m ²	
23°C	12	14	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	85	kJ/m ²	
23°C	80	90	kJ/m ²	
Notched Izod Impact Strength				ISO 180
-30°C	11	12	kJ/m ²	
23°C	12	14	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	260	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	250	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	2.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	1.1E-4	--	cm/cm/°C	
RTI Elec				UL 746
0.750 mm	140	--	°C	
1.50 mm	140	--	°C	
3.00 mm	140	--	°C	
RTI Imp				UL 746
0.750 mm	125	--	°C	
1.50 mm	125	--	°C	
3.00 mm	125	--	°C	
RTI Str				UL 746

0.750 mm	140	--	°C	
1.50 mm	140	--	°C	
3.00 mm	140	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.750 mm)	1.0E+13	--	ohms · cm	IEC 60093
Dielectric Strength (1.00 mm)	20	--	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	PLC 6	--		ASTM D495
Comparative Tracking Index (3.00 mm)	250 to 399	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.750 mm	PLC 0	--		
1.50 mm	PLC 0	--		
3.00 mm	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC 1	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.750 mm	PLC 4	--		
1.50 mm	PLC 3	--		
3.00 mm	PLC 4	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.750 mm	HB	--		
1.50 mm	HB	--		
3.00 mm	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.750 mm	675	--	°C	
1.50 mm	675	--	°C	
3.00 mm	675	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.750 mm	700	--	°C	
1.50 mm	700	--	°C	
3.00 mm	700	--	°C	
Additional Information	Dry	Conditioned		Test Method
Automotive Materials - (thickness d = 1mm)	+	--		FMVSS 302
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0		hr	
Suggested Max Regrind	25		%	
Rear Temperature	280 to 310		°C	

Middle Temperature	280 to 310	°C
Front Temperature	280 to 310	°C
Nozzle Temperature	280 to 310	°C
Processing (Melt) Temp	285 to 305	°C
Mold Temperature	65.0 to 95.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT