Milastomer™ G4502BS

Thermoplastic Vulcanizate

Mitsui Chemicals America, Inc.

Message:

Milastomer™G4502BS is a thermoplastic vulcanized rubber (TPV) material. This product is available in North America and is processed by extrusion. Milastomer™Typical application areas of G4502BS are: coating applications

General Information			
Uses	Coating application		
Appearance	Black		
Forms	Particle		
Processing Method	Extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.920	g/cm³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/10.0 kg)	15	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 5 sec)	48		ISO 48
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ¹ (Break)	13.6	MPa	ISO 37
Tensile Elongation ² (Break)	150	%	ISO 37
Additional Information			
All tests performed according to Mitsui me	ethods.		
NOTE			
1.	500 mm/min		
2.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

