

KEP® 430H

Ethylene Propylene Diene Terpolymer

Kumho Polychem Co., Ltd.

Message:

Features:

Low mooney viscosity & slow vulcanization speed, excellent heat & ozone resistance, optimum scorch safety in blending with IIR

Applications:

Automobile tire tubes, waterproof sheet, heat resistant belt

General Information		
Features	High Heat Resistance	
	Low Viscosity	
	Ozone Resistant	
	Vulcanizable	
Uses	Automotive Applications	
	Belts/Belt Repair	
	Blending	
	Sheet	
Forms	Bale	
Physical	Nominal Value	Unit
Mooney Viscosity (ML 1+4, 125°C)	43	MU
Ethylene Content	57.0	wt%
Ethylidene Norbornene (ENB) Content	1.6	wt%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

