

Delrin® 100STE NC010

ACETAL RESIN

DuPont Performance Polymers

Message:

Super Toughened High Viscosity Acetal Homopolymer with Very Low Emissions

General Information			
Additive	Lubricant		
	Mold Release		
Features	Lubricated		
Uses	Blow Molding Applications		
	Profiles		
	Sheet		
Forms	Pellets		
Processing Method	Blow Molding		
	Coating		
	Extrusion		
	Injection Molding		
	Profile Extrusion		
	Sheet Extrusion		
Part Marking Code (ISO 11469)	>POM-HI<		
Resin ID (ISO 1043)	POM-HI		
Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.3	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	2.00	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1300	MPa	ISO 527-2
Tensile Stress (Yield)	43.0	MPa	ISO 527-2
Tensile Strain (Yield)	33	%	ISO 527-2
Nominal Tensile Strain at Break	> 50	%	ISO 527-2
Flexural Modulus	1250	MPa	ISO 178
Flexural Stress (3.5% Strain)	35.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	17	kJ/m ²	

23°C	90	kJ/m ²	
Charpy Unnotched Impact Strength		ISO 179/1eU	
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	111	°C	ISO 75-2/B
1.8 MPa, Unannealed	64.0	°C	ISO 75-2/A
Melting Temperature ¹	178	°C	ISO 11357-3
Additional Information	Nominal Value	Unit	Test Method
Emission	< 2.00	mg/kg	VDA 275
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT