# Spartech Polycom SC7-70910

## Polycarbonate

## Spartech Polycom

# Message:

Spartech SC7-70910 is a medium viscosity, reprocessed, PC resin for injection molding. It is heat stabilized and lubricated for good processing characteristics.

Polycarbonate resins span a wide range of physical properties that combine to make it one of the toughest, most versatile of all engineering thermoplastics. It is well known for its exceptional impact resistance, plus it has outstanding mechanical, electrical, and optical properties. A very versatile product for a wide variety of applications, Spartech SC7-70910 is recommended for industrial, transportation, sporting goods and electrical/electronic applications.

General Information				
Additive	heat stabilizer Lubricant			
Recycled Content	Yes			
Features	Impact resistance, high			
	Workability, good			
	Good electrical performance			
	Thermal Stability			
	Thermal stability, good			
	Good toughness			
	Lubrication			
	Medium viscosity			
Uses	Electrical/Electronic Applications			
	Industrial application			
	Application in Automobile Field			
	Sporting goods			
Appearance	Available colors			
	Natural color			
Forms	Particle			
Processing Method	Injection molding			
Physical	Nominal Value	Unit	Test Method	
Melt Mass-Flow Rate (MFR)	20	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (23°C)	63.8	MPa	ASTM D638	
Flexural Modulus (23°C)	2070	MPa	ASTM D790	
Flexural Strength (23°C)	91.4	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
-				

Notched Izod Impact (23°C)	130	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	3.0 - 4.0	hr	
Rear Temperature	266 - 277	°C	
Middle Temperature	271 - 282	°C	
Front Temperature	282 - 299	°C	
Nozzle Temperature	277 - 304	°C	
Processing (Melt) Temp	288 - 316	°C	
Mold Temperature	71.1 - 93.3	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

