

Generic SBR, Solution

Solution Styrene Butadiene Rubber

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic SBR, Solution
This information is provided for comparative purposes only.

General Information			
Physical	Nominal Value	Unit	Test Method
Mooney Viscosity	47 to 61	MU	ASTM D1646
Bound Styrene	23.3 to 25.5	%	
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-30.9 to -5.88	°C	DSC

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT