

Vexel PBT B12GF30 SA

Polybutylene Terephthalate

Custom Resins Group

Message:

30% glass fiber reinforced PBT specially formulated for improved surface appearance

Has the high chemical and heat resistance of PBT combined with high strength and stiffness

Suitable for tool and appliance housings, levers, sunroof components and other uses which require high mechanical properties and good appearance

General Information	
Filler / Reinforcement	Glass Fiber,30% Filler by Weight
Features	Good Chemical Resistance
	High Heat Resistance
	High Stiffness
	High Strength
	Pleasing Surface Appearance
Uses	Appliance Components
	Housings

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	121	MPa	ASTM D638
Flexural Modulus	8270	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	85	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	210	°C	
1.8 MPa, Unannealed	207	°C	
Peak Melting Temperature	227	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

