

# UNIVAL™ DMDA-6230 NT 7

High Density Polyethylene Resin

The Dow Chemical Company

## Message:

Outstanding environmental stress crack resistance

High impact strength

Good extrusion characteristics

Complies with:

U.S. FDA 21 CFR 177.1520 (c) 3.2a

U.S. FDA-DMF

U.S. USP Class VI

Canadian HPFB No Objection (With Limitations)

Underwriters Laboratories, Inc.

Consult the regulations for complete details.

UNIVAL™ DMDA-6230 NT 7 High Density Polyethylene (HDPE) Resin is specifically designed for use in either intermittent or continuous blow molding equipment to produce containers up to 20 gallons in size - applications that require the combination of outstanding environmental stress crack resistance (ESCR) and, high impact strength. UNIVAL DMDA- 6230 NT 7 HDPE resin is also considered a multipurpose blow molding resin designed for the high speed production of blow molded containers used for packaging household industrial chemicals (e.g., detergents, bleach, fabric softeners), toiletries and cosmetics (e.g., shampoos, creams, lotions, etc.), health and medicinal aids. In addition, it can be blow molded into other thin walled parts and houseware items, and also can be extruded into profiles or sheets.

General Information			
UL YellowCard	E337483-100655679		
Agency Ratings	DMF not rated		
	FDA 21 CFR 177.1520(c) 3.2a		
	HPFB (Canada) No Objection 3		
	UL 94		
	USP Class VI		
Forms	Particle		
Processing Method	Blow molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.949	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR)			ASTM D1238
190°C/2.16 kg	0.25	g/10 min	ASTM D1238
190°C/21.6 kg	25	g/10 min	ASTM D1238
Environmental Stress-Cracking Resistance (50°C, 100% Igepal, F50)	180	hr	ASTM D1693
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	57		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	23.4	MPa	ASTM D638
Fracture	31.0	MPa	ASTM D638
Tensile Elongation			ASTM D638

Yield	8.0	%	ASTM D638
Fracture	900	%	ASTM D638
Flexural Modulus - 2% Secant	910	MPa	ASTM D790B
Impact	Nominal Value	Unit	Test Method
Tensile Impact Strength <sup>1</sup>	210	kJ/m <sup>2</sup>	ASTM D1822
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	62.0	°C	ASTM D648
Brittleness Temperature	< -76.0	°C	ASTM D746
Vicat Softening Temperature	127	°C	ASTM D1525
Melting Temperature (DSC)	130	°C	Internal method
Peak Crystallization Temperature (DSC)	118	°C	Internal method
Additional Information			
根据 ASTM D 4976 进行基板模制和测试.			
NOTE			

1. Type s

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

