# Geon™ Vinyl Flexible A8504

#### Flexible Polyvinyl Chloride

### PolyOne Corporation

#### Message:

Geon™ Vinyl Flexible A8504 is a Flexible Polyvinyl Chloride product. It can be processed by extrusion, injection molding, or profile extrusion and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Applications of Geon™ Vinyl Flexible A8504 include hose/tubing, appliances and plumbing/piping/potable water. Primary characteristic: high gloss.

General Information			
Features	General Purpose		
	High Gloss		
Uses	Appliances		
	General Purpose		
	Hose		
	Tubing		
Agency Ratings	NSF 61 2		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	85		
Shore A, 15 sec	79		
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup>			ASTM D638
Break	16.9	MPa	
100% Strain	10.3	MPa	
Tensile Elongation <sup>2</sup> (Break)	380	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength <sup>3</sup>	73.6	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-32.8	°C	ASTM D746
Injection	Nominal Value	Unit	
Processing (Melt) Temp	188 to 199	°C	

Extrusion	Nominal Value	Unit	
Melt Temperature	174 to 179	°C	
NOTE			
1.	510 mm/min		
2.	510 mm/min		
3.	Die C, 510 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

