

Elvax® 3134SBZ

Ethylene Vinyl Acetate Copolymer
DuPont Packaging & Industrial Polymers

Message:

DuPont™ Elvax® 3134SBZ is an extrudable ethylene-vinyl acetate copolymer resin available in pellet form for use in conventional extrusion equipment designed to process polyethylene resins.

Composition

12% By Weight Vinyl Acetate

Slip Additive, Antiblock additive

Thermal Stabilizer: non-BHT antioxidant

Applications

This resin is designed to provide a low temperature heat seal to itself or many other materials commonly used in flexible packaging applications. The melt properties of this resin allow it to be processed on extrusion coating and cast film equipment over a wide range of line speeds and film thicknesses. Typically, cast film of this grade is adhesive laminated to polyester or other substrates as required by the application.

General Information	
Additive	Antiblock
	Antioxidant
	Heat Stabilizer
	Slip
Features	Antiblocking
	Antioxidant
	Copolymer
	Food Contact Acceptable
	Good Flexibility
	Good Heat Seal
	Heat Stabilized
	Low Temperature Heat Sealability
Uses	Slip
	Cast Film
	Coating Applications
	Film
Agency Ratings	Packaging
	FDA 21 CFR 177.1350(a)(1)
Forms	Pellets
Processing Method	Cast Film
	Coextruded Film
	Coextrusion
	Extrusion Coating
	Film Extrusion

Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.930	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	8.0	g/10 min	ASTM D1238, ISO 1133
Vinyl Acetate Content	12.0	wt%	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	71.0	°C	ASTM D1525, ISO 306
Melting Temperature (DSC)	95.0	°C	ASTM D3418, ISO 3146
Freezing Point ¹			
--	76	°C	ASTM D3418
--	76	°C	ISO 3146
Extrusion	Nominal Value	Unit	
Melt Temperature	< 230	°C	
NOTE			
1.	DSC		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT