

# Biorene® HA-40

Polystyrene Alloy  
Resirene, S.A. de C.V.

Message:  
A hybrid resin between PS and Starch with excellent mechanical and thermal properties.

General Information			
Features	Renewable Resource Content		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	9.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	773	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	20.0	MPa	
Break	17.0	MPa	
Tensile Elongation			ASTM D638
Yield	5.0	%	
Break	3.0	%	
Injection	Nominal Value	Unit	
Processing (Melt) Temp	140 to 180	°C	
Mold Temperature	40.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT