

TABOREN PC 63 T 20

Polypropylene Copolymer

SILON s.ro

Message:

TABOREN PC 63 T 20 is a Polypropylene Copolymer (PP Copolymer) product filled with 20% talc. It is available in Asia Pacific or Europe. Applications of TABOREN PC 63 T 20 include electrical/electronic applications and outdoor applications.

Characteristics include:

Copolymer

Good UV Resistance

UV Stabilized

General Information			
Filler / Reinforcement	Talc,20% Filler by Weight		
Additive	UV Stabilizer		
Features	Copolymer		
	Good UV Resistance		
Uses	Electrical/Electronic Applications		
	Outdoor Applications		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	12	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	24.0	MPa	ISO 527-2/1B/50
Flexural Modulus	2500	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	150	°C	ISO 306/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT