

# Hanwha Total PP FH43

Polypropylene

HANWHA TOTAL PETROCHEMICALS Co., Ltd.

## Message:

FH43 is a polypropylene that features superior flame retardancy, rigidity and impact - resistance. This product is widely used for TV D/Y, and for the exterior parts of electronic products due to superior thermo-plasticity.

General Information			
UL YellowCard	E140331-222920		
Additive	heat stabilizer		
Features	Good dimensional stability		
	Rigidity, high		
	Impact resistance, high		
	Heat resistance, high		
	Thermal Stability		
	Thermal stability, good		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Electrical components		
	Shell		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	9.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (2.00 mm)	1.0 - 1.4	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	95		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>1</sup> (Yield)	30.4	MPa	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	30	%	ASTM D638
Flexural Modulus <sup>3</sup>	2750	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	41	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	133	°C	ASTM D648
Flammability	Nominal Value		Test Method

Flame Rating (0.794 mm)	V-0	UL 94
Injection	Nominal Value	Unit
Rear Temperature	170 - 180	°C
Middle Temperature	180 - 200	°C
Front Temperature	180 - 200	°C
Nozzle Temperature	190 - 200	°C
Mold Temperature	40.0 - 70.0	°C
Injection Pressure	39.2 - 78.5	MPa
Back Pressure	0.490 - 1.96	MPa
Injection instructions		
Injection Speed: 50 to 80 %		
NOTE		
1.	50 mm/min	
2.	50 mm/min	
3.	5.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

