

Elastoflex® R 27640R Resin / R 27640T

Isocyanate

Polyurethane (MDI)

BASF Corporation

Message:

Semi-Rigid Low VOC Instrument Panel Foam

General Information		
Features	Semi Rigid	
	Low VOC	
Uses	Foam	
	Application in Automobile Field	
	Car dashboard	
Physical	Nominal Value	Unit
Density		
-- 1	0.106	g/cm ³
-- 2	0.124	g/cm ³
Mechanical	Nominal Value	Unit
Tensile Strength		
-- 3	0.272	MPa
-- 4	0.367	MPa
Tensile Elongation		
Fracture ⁵	60	%
Fracture ⁶	67	%
Films	Nominal Value	Unit
Graves Tear		
-- 7	840.6	N/m
-- 8	1225.9	N/m
NOTE		
1.	Hand Mix	
2.	Machine Mix	
3.	Hand Mix	
4.	Machine Mix	
5.	Hand Mix	
6.	Machine Mix	
7.	Hand Mix	
8.	Machine Mix	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

