

LAMINEX® 2010

Phenol Formaldehyde Resin

Schwartz Technical Plastic

Message:

Finely woven cotton fabric, phenolic resin impregnated

Applications:

Rollneck-bearings

Slippers

Inserts for coupling boxes

General Information			
Uses	Fabric		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	170	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7000	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	80.0	MPa	ISO 527-2
Fracture	100 - 130	MPa	ISO 527-2
Compressive Stress	170	MPa	ISO 604
Coefficient of Friction			ASTM D1894
With steel-static ¹	0.020		ASTM D1894
With steel-static ²	0.020		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	15	kJ/m ²	ISO 180
Unnotched Izod Impact Strength	30	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	3.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity	0.29	W/m/K	ISO 8302
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+8	ohms	IEC 60093
Dielectric Constant	5.00		IEC 60250
Dissipation Factor	0.30		IEC 60250

Additional Information	
Creepage/leakage Resistance: KA1Safe Temperature Range, short periods: 150°CSafe Temperature Range, permanent: 120°CMoisture Absorption under normal air condition: 100 mg	

NOTE	
1.	without lubrication
2.	with lubrication

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

