# **TAISOX 8010**

### High Density Polyethylene

## Formosa Plastics Corporation

#### Message:

TAISOX 8010 is a high density polyethylene material. This product is available in North America, Europe or Asia Pacific. The processing method is extrusion.

The main features of TAISOX 8010 are:

Good processability

Impact resistance

Typical application areas include:

bag/lining

sheet

Sling/Rope

Foam

Yarn

General Information				
Features	High density			
	Impact resistance, high			
	Workability, good			
	Good stretchability			
Uses	Bags			
	Monochrome high toughness line			
	Foam			
	Sheet			
	Rope			
	Web			
Гоимо	Particle			
Forms				
Processing Method	Extrusion			
Physical	Nominal Value	Unit	Test Method	
Density	0.956	g/cm³	ASTM D1505	
Melt Mass-Flow Rate (MFR) (190°C/2.16				
kg)	1.0	g/10 min	ASTM D1238	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D)	69		ASTM D2240	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength			ASTM D638	
Yield	28.9	MPa	ASTM D638	
Fracture	38.2	MPa	ASTM D638	
Tensile Elongation (Break)	1000	%	ASTM D638	
Impact	Nominal Value	Unit	Test Method	
Tensile Impact Strength	343	kJ/m²	ASTM D1822	

Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-70.0	°C	ASTM D746
Vicat Softening Temperature	127	°C	ASTM D1525
Melting Temperature	134	°C	
Additional Information			

Notched Izod Impact Strength, ASTM D256: 50 kg-cm/cm²Injection Melt Temperature Yarn: 190 to 210°CInjection Melt Temperature Monofilament: 260 to 280°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

