

SPESIN® KP212V0BLK

Polybutylene Terephthalate

Kolon Plastics, Inc.

Message:

SPESIN® KP212V0BLK is a Polybutylene Terephthalate (PBT) product. It is available in Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Flame Rated

Flame Retardant

General Information			
UL YellowCard	E190675-100647282		
Additive	Flame Retardant		
Features	Flame Retardant		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.42	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.8 to 2.6	%	ASTM D955
Water Absorption (Equilibrium, 23°C, 60% RH)	0.060	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	60.0	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	11	%	ASTM D638
Flexural Modulus (23°C)	2630	MPa	ASTM D790
Flexural Strength (23°C)	98.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	35	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	165	°C	
1.8 MPa, Unannealed	55.0	°C	
Peak Melting Temperature	224	°C	ASTM D1525
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	25	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.20		ASTM D150
Arc Resistance	85.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

