# THERMOLAST® K TC7WEZ (Series: UV/HF)

#### Thermoplastic Elastomer

### **KRAIBURG TPE**

#### Message:

The UV/HF Series is your material solution for applications requiring high UV resistance and high flow ability. It is particularly appropriate for automotive exterior components.

Typical applications

Cowls gaskets

Roof rims

Water deflectors

Window encapsulations

Material advantages

Easy flowing

Excellent processing behavior

Perfect adhesion to PP

Tested according PV3930 for outdoor use

General Information				
Features	Good UV resistance			
	Workability, good			
	Good adhesion			
	High liquidity			
Uses	Washer			
	Application in Automobile Field			
	Automotive exterior parts			
Appearance	Black			
Processing Method	Injection molding			
Physical	Nominal Value	Unit	Test Method	
Density	0.930	g/cm³	ISO 1183	
Spiral Flow	95.0	cm		
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A)	72		ISO 7619	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress <sup>1</sup> (Break)	8.00	MPa	ISO 37	
Tensile Elongation <sup>2</sup> (Break)	600	%	ISO 37	
Tear Strength <sup>3</sup>	20	kN/m	ISO 34-1	
Injection	Nominal Value	Unit		
Drying Temperature	60 - 80	°C		
Drying Time	2.0 - 4.0	hr		
Rear Temperature	180	°C		
Middle Temperature	200	°C		
Front Temperature	220	°C		

Mold Temperature	25 - 40	°C	
Injection Pressure	20.0 - 100	MPa	
Back Pressure	2.00 - 10.0	MPa	
NOTE			
1.	Type S2, 200 mm/min		
2.	Type S2, 200 mm/min		
	Method B, right-angle sp	ecimen	
3.	(cut)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519 Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

