

# MTEGRITY™ LLDPE LL104AH

Linear Low Density Polyethylene

M. Holland Company

## Message:

Linear Low Density Polyethylene  
No Slip  
High Antiblock  
Commercial and Industrial packaging  
Liners

General Information			
Additive	High caking resistance		
Features	Low density		
	High caking resistance		
Uses	Packaging		
	Films		
	Lining		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	0.922	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
MD	200	MPa	ASTM D882
TD	230	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Fracture	49.0	MPa	ASTM D882
TD: Fracture	33.8	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	540	%	ASTM D882
TD: Fracture	830	%	ASTM D882
Dart Drop Impact	100	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	100	g	ASTM D1922
TD	330	g	ASTM D1922

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

