## Actymer® AE-2080S

## Thermoplastic Vulcanizate

Riken Technos Corp.

## Message:

Actymer®AE-2080S is a thermoplastic vulcanized rubber (TPV) product. It is available in North America or Asia Pacific. Features include: chemical resistance Heat resistance

| General Information   |                       |       |             |
|---|-----------------------|-------|-------------|
| Features  | High elasticity       |       |             |
|   | Heat resistance, high |       |             |
|   | Oil resistance        |       |             |
|   |                       |       |             |
| Forms   | Particle              |       |             |
| Physical  | Nominal Value         | Unit  | Test Method |
| Density   | 0.938                 | g/cm³ | ISO 1183    |
| Hardness  | Nominal Value         | Unit  | Test Method |
| Durometer Hardness (Shore A, 15 sec)                        | 80                    |       | ISO 868     |
| Elastomers  | Nominal Value         | Unit  | Test Method |
| Tensile Stress (100% Strain)                                | 3.80                  | MPa   | ISO 37      |
| Tensile Stress (Yield)                                      | 17.7                  | MPa   | ISO 37      |
| Tensile Elongation (Break)                                  | 780                   | %     | ISO 37      |
| Tear Strength   | 45                    | kN/m  | ISO 34-1    |
| Compression Set   |                       |       | ISO 815     |
| 70°C, 72 hr   | 51                    | %     | ISO 815     |
| 120°C, 72 hr  | 63                    | %     | ISO 815     |
| Aging   | Nominal Value         | Unit  | Test Method |
| Change in Tensile Strength in Air (136°C,<br>168 hr)        | 0.0                   | %     | ISO 188     |
| Change in Tensile Strain at Break in Air<br>(136°C, 168 hr) | 0.0                   | %     | ISO 188     |
| Thermal   | Nominal Value         | Unit  | Test Method |
| Brittleness Temperature                                     | -60.0                 | °C    | ISO 974     |
| Additional Information                                      |                       |       |             |

The values listed above are tested in accordance with JIS K test methods.Rebound Resilience: 48%

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

