

ISOPAK® 525GF17

Acrylonitrile Butadiene Styrene

Great Eastern Resins Industrial Co., Ltd. (GRECO)

Message:

Surface Modified, Good Flow

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 17% filler by weight		
Features	Good liquidity		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	7.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.15	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	6180	MPa	ASTM D638
Tensile Strength ²	71.4	MPa	ASTM D638
Tensile Elongation ³ (Break)	1.7	%	ASTM D638
Flexural Modulus	3990	MPa	ASTM D790
Flexural Strength	90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (25°C, 0.125 mm)	88	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	96.0	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	80	°C	
Drying Time	2.0 - 3.0	hr	
Processing (Melt) Temp	200 - 230	°C	
Mold Temperature	70 - 90	°C	
NOTE			
1.	5.0 mm/min		
2.	5.0 mm/min		
3.	5.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

