

Clariant Nylon 6/12 612G13-L

Polyamide 612
Clariant Corporation

Message:

Clariant Nylon 6/12 612G13-L is a Polyamide 612 (Nylon 612) material filled with 13% glass fiber. It is available in North America for injection molding. Primary attribute of Clariant Nylon 6/12 612G13-L: Lubricated.

General Information			
Filler / Reinforcement	Glass Fiber,13% Filler by Weight		
Additive	Lubricant		
Features	General Purpose		
	Lubricated		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.50	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	75.8	MPa	ASTM D638
Tensile Elongation (Break)	7.0	%	ASTM D638
Flexural Modulus	3450	MPa	ASTM D790
Flexural Strength	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	43	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	193	°C	
1.8 MPa, Unannealed	91.1	°C	
Melting Temperature	212	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT