KetaSpire® KT-880 GF15

Polyetheretherketone

Solvay Specialty Polymers

Message:

KetaSpire[®] KT-880 GF15 is a high flow, 15% glass-fiber reinforced grade of polyetheretherketone (PEEK). This resin offers higher strength and stiffness properties relative to unreinforced KetaSpire[®] PEEK resin. The glass fiber content is optimized to provide a balance of strength and stiffness with toughness-related properties, such as impact resistance and elongation at break. The low fiberglass loading gives the resin improved surface aesthetics and reduced anisotropy over comparable 30% glass reinforced formulations.

KetaSpire® PEEK is produced to the highest industry standards and is characterized by a distinct combination of properties, which include excellent wear resistance, best-in-class fatigue resistance, ease of melt processing, high purity and excellent chemical resistance to organics, acids and bases. These properties make it well-suited for applications in oil & gas, healthcare, transportation, electronics, chemical processing and other industrial uses. Natural: KT-880 GF15 NT

General Information	
Filler / Reinforcement	Glass Fiber,15% Filler by Weight
Features	Autoclave Sterilizable
	Biocompatible
	E-beam Sterilizable
	Ethylene Oxide Sterilizable
	Fatigue Resistant
	Flame Retardant
	Good Chemical Resistance
	Good Dimensional Stability
	Good Sterilizability
	Heat Sterilizable
	High Flow
	High Heat Resistance
	High Stiffness
	High Strength
	Radiation (Gamma) Resistant
	Radiation Sterilizable
	Radiotranslucent
	Steam Resistant
	Steam Sterilizable
Uses	Aircraft Applications
	Automotive Applications
	Connectors
	Dental Applications

Electrical/Electronic Applications

Film

Hospital Goods

Industrial Applications
Medical Devices
Medical/Healthcare Applications
Oil/Gas Applications
Pump Parts
Seals

. . .

Surgical Instruments

RoHS Compliance	Contact Manufacturer		
Appearance	Tan		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.41	g/cm³	ASTM D792
Ash Content	15	%	ISO 3451-1
Modulus of Elasticity	6.61	GPa	ASTM D638
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6700	MPa	ASTM D638
Tensile Stress (Break)	138	MPa	ASTM D638
Tensile Strain ¹ (Break)	5.0	%	ASTM D638
Flexural Stress	231	MPa	ASTM D638
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	53	kJ/m²	ISO 179
Notched Izod Impact			
	47	J/m	ASTM D256
	5.0	kJ/m²	ISO 180
Unnotched Izod Impact	660	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	278	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	150	°C	
Drying Time	4.0	hr	
Rear Temperature	365	°C	
Middle Temperature	371	°C	
Front Temperature	377	°C	
Nozzle Temperature	382	°C	
Mold Temperature	177 to 204	°C	
Injection Rate	Fast		
Screw Compression Ratio	2.5:1.0 to 3.5:1.0		
NOTE			

1.

Type 1A, 5 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

