

Hoffman PVC V7-54

Rigid Polyvinyl Chloride
Hoffman Plastic Compounds Inc.

Message:

Hoffman PVC V7-54 is a rigid polyvinyl chloride material. This product is available in North America. The processing method is: profile extrusion molding. The main characteristics of Hoffman PVC V7-54 are:

flame retardant/rated flame

Hard

Impact resistance

General Information			
Features	Rigidity, high		
	Medium impact resistance		
Forms	Particle		
Processing Method	Profile extrusion molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.39	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.30 - 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	80		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2620	MPa	ASTM D638
Tensile Strength	45.5	MPa	ASTM D638
Flexural Modulus	2760	MPa	ASTM D790
Flexural Strength	75.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	530	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Annealed)	68.9	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating	V-0		UL 94
Extrusion	Nominal Value	Unit	
Melt Temperature	149 - 166	°C	
Extrusion instructions			

The processing temperature given is for a standard nozzle tip and screw. The temperature range for a smear nozzle tip and PVC screw is 330 - 360°F.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

