

DENKA ABS APG-3000

Acrylonitrile Butadiene Styrene

Denka Company Limited

Message:

DENKA ABS APG-3000 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Asia Pacific, Europe, or North America.

General Information			
Features	Antistatic		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.04	g/cm ³	ASTM D792
23°C	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	23	g/10 min	ISO 1133
Molding Shrinkage (2.00 mm)	0.50 to 0.70	%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	95		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	38.0	MPa	ASTM D638
--	2200	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	40.0	MPa	
Break	30.0	MPa	
Nominal Tensile Strain at Break	30	%	ISO 527-2/50
Flexural Modulus			
-- ²	1900	MPa	ASTM D790
-- ³	1930	MPa	ISO 178
Flexural Strength			
-- ⁴	57.0	MPa	ASTM D790
-- ⁵	60.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	33	kJ/m ²	ISO 179
Notched Izod Impact	340	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed ⁶	84.0	°C	ASTM D648
1.8 MPa, Unannealed	75.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	90.0	°C	ASTM D1525 ⁷

--	91.0	°C	ISO 306/B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ⁸	1.0E+10	ohms	JIS K6911
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	180 to 200	°C	
Middle Temperature	200 to 230	°C	
Front Temperature	210 to 260	°C	
Nozzle Temperature	210 to 255	°C	
Mold Temperature	40.0 to 60.0	°C	
Back Pressure	0.490 to 0.981	MPa	
Screw Speed	80 to 120	rpm	
NOTE			
1.	5.0 mm/min		
2.	15 mm/min		
3.	2.0 mm/min		
4.	15 mm/min		
5.	2.0 mm/min		
6.	Edgewise		
7.	Loading 2 (50 N)		
8.	23°C, 50% RH		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

