Moplen RP5051

Polypropylene Random Copolymer PolyMirae

Message:

"Moplen" RP5051 is a controlled rheology slightly propylene random copolymer for manufacturing high transparent cast films. The product contains slipand antiblock agents. It exhibits very good optical properties and good heat weldability. Main applications are packaging of foodstuffs such as sweets, pasta, biscuits and snacks, packaging of books, stationary, blankets, shirts and hosiery. "Moplen" RP5051 is suitable for food contact.

General Information			
Additive	Antiblock		
	Slip		
Features	Antiblocking		
	Controlled Rheology		
	High Clarity		
	Opticals		
	Random Copolymer		
	Slip		
	Weldable		
Uses	Cast Film		
	Food Packaging		
	Packaging		
	Stationary Supplies		
Appearance	Clear/Transparent		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm³	ISO 1183, ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.		40 :	ACTNA D4000 ICO 4400
kg)	8.0	g/10 min	ASTM D1238, ISO 1133
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	85	11.21	ASTM D785
Mechanical To the Standard Library	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	24.5	MPa	ASTM D638
Tensile Elongation (Yield)	12	%	ASTM D638
Flexural Modulus	705	MD-	ACTNA DZOO
	785	MPa	ASTM D790
	780	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA

0°C	0.40	kJ/m²	
23°C	3.0	kJ/m²	
Charpy Unnotched Impact Strength			ISO 179/1eU
0°C	130	kJ/m²	
23°C	No Break		
Notched Izod Impact (23°C)	49	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0).45		
MPa, Unannealed)	90.0	°C	ASTM D648
Vicat Softening Temperature	130	°C	ISO 306/A50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

