

UNIPA® Im

Polyamide 612

Nytec Plastics, Ltd.

Message:

Since its introduction in 1938, Nylon has become one of the world's most widely recognized and utilized engineering grade thermoplastics. Nylon's unique combination of high strength, good toughness, outstanding chemical resistance, and excellent wear and abrasion resistance have made it the material of choice for product designs in a multitude of industries. When used to replace wear grade metals like brass and bronze, no other material provides the combination of extended wear life, light weight, and low fabricated part cost of Nylon. Nytec Plastics, Ltd. manufactures UNIPA® Nylon stock shapes in a wide variety of types and stock shape configurations. These UNIPA Nylon products fall into the categories of Type 6/6 Extruded UNIPA Nylons and Type 6 UNIPA M Cast Nylons. While both types of Nylon are very similar, there are performance and availability differences between the two grades that should be noted:

UNIPA Type 6/6 Extruded Nylons:

offer improved toughness

offer improved flame resistance

are available in smaller rod diameters (< 2" dia.)

Nytec Plastic's UNIPA Nylon 6/6 extruded stock shapes are available in a wide range of grades— including both lubricated and fiber reinforced products.

UNIPA Nylon 6/6 materials are offered in a complete range of extruded round, square, and hex rod, heavy gauge plate, and tubular bar sizes.

General Information	
Features	Flame Retardant
	Good Abrasion Resistance
	Good Chemical Resistance
	Good Toughness
	Good Wear Resistance
	High Impact Resistance
	High Stiffness
	High Strength
	Low Moisture Absorption
	Machinable
Uses	Automotive Applications
	Bearings
	Bushings
	Construction Applications
	Electrical Parts
	Electrical/Electronic Applications
	Fluid Handling
	Food Service Applications
	Gears
	Mining Applications
	Molds/Dies/Tools
	Pulleys
	Pump Parts
	Rollers

Textile Applications

Valves/Valve Parts

Wear Strip

Wheels

Forms	Preformed Parts		
	Rod		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.06	g/cm ³	ASTM D792
Water Absorption			ASTM D570
24 hr	0.25	%	
Saturation	3.0	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2240	MPa	ASTM D638
Tensile Strength	55.2	MPa	ASTM D638
Tensile Elongation (Break)	200	%	ASTM D638
Flexural Modulus	2070	MPa	ASTM D790
Flexural Strength	96.5	MPa	ASTM D790
Compressive Strength	107	MPa	ASTM D695
Coefficient of Friction	0.30		ASTM D1894
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	64	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	65.0	°C	ASTM D648
Continuous Use Temperature	93.3	°C	Internal Method
Peak Melting Temperature	217	°C	ASTM D3418
CLTE - Flow	9.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+13	ohms · cm	ASTM D257
Dielectric Constant			ASTM D150
1 MHz	4.00		
60 MHz	6.00		
Dissipation Factor (60 Hz)	0.15		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT