

# Avalon 57

Polytetrafluoroethylene  
Greene, Tweed & Co.

Message:

Thermoset Resin Filled

General Information			
Filler / Reinforcement	Filler		
Appearance	Light Brown Tan		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.01	g/cm <sup>3</sup>	ASTM D1457
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	17.9	MPa	ASTM D1457
Tensile Elongation (Break)	300	%	ASTM D1457
Coefficient of Friction			
vs. Itself - Dynamic <sup>1</sup>	0.17		
vs. Itself - Static <sup>2</sup>	0.25		
Deformation Under Load (26°C, 14 MPa)	2.30	%	ASTM D621
Wear Factor	9.3	10 <sup>-8</sup> mm <sup>3</sup> /N·m	ASTM D3702
NOTE			
1.	33.3 psi, 150 fpm		
2.	33.3 psi		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT