

RTP 199 X 143686 A BLACK

Polypropylene
RTP Company

Message:
Cellulose Fiber - 20% Renewable Resource Content - Additional 67% Post Consumer Recycled Content

General Information			
Filler / Reinforcement	Fiber filler		
Features	Updatable resources		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.00	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.30 - 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1720	MPa	ASTM D638
Tensile Strength	34.5	MPa	ASTM D638
Tensile Elongation (Yield)	4.0 - 7.0	%	ASTM D638
Flexural Modulus	1860	MPa	ASTM D790
Flexural Strength	48.3	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	530	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	122	°C	ASTM D648
1.8 MPa, not annealed	62.2	°C	ASTM D648
Additional Information	Nominal Value	Unit	
Renewable Content	20	%	
Injection	Nominal Value	Unit	
Drying Temperature	79	°C	
Drying Time	2.0	hr	
Processing (Melt) Temp	191 - 232	°C	
Mold Temperature	32 - 66	°C	
Injection Pressure	68.9 - 103	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

