

HAIPLEN EP60 T5

Polypropylene Copolymer

Taro Plast S.p.A.

Message:

HAIPLEN EP60 T5 is a polypropylene copolymer (PP Copoly) product, which contains 25% talc filler. It can be processed by injection molding and is available in Europe.

- Features include:
- flame retardant/rated flame
 - Copolymer
 - heat stabilizer
 - UV stability

General Information			
Filler / Reinforcement	Talc filler, 25% filler by weight		
Additive	heat stabilizer		
	UV stabilizer		
Features	Copolymer		
	Laser marking		
	Detergent resistance		
	Thermal Stability		
Appearance	Available colors		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.17	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ASTM D955
Flow	1.0	%	ASTM D955
Transverse flow	1.0	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.050	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	30.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	20	%	ASTM D638, ISO 527-2
Flexural Modulus	2100	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	30	J/m	ASTM D256
0°C	40	J/m	ASTM D256
23°C	50	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, not annealed	130	°C	ASTM D648, ISO 75-2/B
1.8 MPa, not annealed	60.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature			
--	152	°C	ASTM D1525, ISO 306/A50 1 ¹
--	80.0	°C	ASTM D1525, ISO 306/B50 2 ²
CLTE - Flow	6.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Additional Information			
Notched Izod Impact Strength , ISO 180, 23°C: 50 J/mNotched Izod Impact Strength , ISO 180, -20°C: 30 J/mNotched Izod Impact Strength , ISO 180, 0°C: 40 J/mMelt Mass-Flow Rate , ISO 1133, 230/2.16 kg: 14 to 18 g/10minMelt Mass-Flow Rate , ASTM D1238, 230/2.16 kg: 14 to 18 g/10minCTI IEC 112, IEC 60112, Method A: >600 V			
Injection	Nominal Value	Unit	
Drying Temperature	70.0 - 80.0	°C	
Drying Time	1.0	hr	
Processing (Melt) Temp	190 - 230	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Fast		
NOTE			
1.	速率 A (50°C/h), 压 力1 (10N)		
2.	速率 A (50°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT