

Silamid® LS

Polyamide 6
Roonamid a.s.

Message:

Polyamide 6, modified, increased impact toughness maintained even at low temperature and dry conditions, optimal processing properties, natural, other color shades according to customer's request. Suitable as a construction material where an increased impact strength is required.

General Information			
Additive	Impact Modifier		
Features	Good Impact Resistance		
	Good Processability		
	Good Toughness		
	Impact Modified		
	Low Temperature Toughness		
Uses	Construction Applications		
Appearance	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.07	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ISO 1133
Molding Shrinkage			
Across Flow	1.7	%	
Flow	1.6	%	
Water Absorption (23°C, 24 hr)	1.5	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1600	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	45.0	MPa	
Break	35.0	MPa	
Flexural Modulus	1400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°C	15	kJ/m ²	
23°C	50	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-40°C	No Break		

23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	100	°C	ISO 75-2/B
1.8 MPa, Unannealed	40.0	°C	ISO 75-2/A
Injection	Nominal Value	Unit	
Drying Temperature	< 80.0	°C	
Suggested Max Moisture	0.10	%	
Processing (Melt) Temp	230 to 250	°C	
Mold Temperature	60.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

